



Flexterra[®] HP-FGM[™]

High Performance Flexible Growth Medium



Description

Flexterra[®] HP-FGM[™] is a fully biodegradable, High Performance-Flexible Growth Medium (HP-FGM) composed of 100% recycled and Thermally Refined[™] wood fibers, crimped interlocking man-made biodegradable fibers, micro-pore granules, naturally derived cross-linked biopolymers and water absorbents. The HP-FGM is phyto-sanitized, free from plastic netting, requires no curing period and upon application forms an intimate bond with the soil surface to create a continuous, porous, absorbent and flexible erosion resistant blanket that allows for rapid germination and accelerated plant growth.

Recommended Applications

- Erosion control for slopes ranging from mild to severe ($\leq 0.25H:1V$)
- Rough graded slopes
- Superior performance over rolled erosion control blankets with plastic nettings
- Enhancement of vegetation establishment
- Ideal infill material to create the GreenArmor[™] System

Technical Data

Physical Properties*	Test Method	Units	Minimum Value
Mass/Unit Area	ASTM D6566 ¹	g/m ² (oz/yd ²)	407 (12)
Thickness	ASTM D6525 ¹	mm (in)	5.6 (0.22)
Wet Bond Strength	ASTM D6818 ¹	N/m (lb/ft)	131 (9)
Ground Cover	ASTM D6567 ¹	%	99
Water Holding Capacity	ASTM D7367	%	1700
Material Color	Observed	n/a	Green
Performance Properties*	Test Method	Units	Value
Cover Factor ²	Large Scale ⁴	n/a	< 0.01
Percent Effectiveness ³	Large Scale ⁴	%	> 99
Cure Time	Observed	hours	0 - 2
Vegetation Establishment	ASTM D7322 ¹	%	800
Environmental Properties*	Test Method	Units	Typical Value
Functional Longevity ⁵	ASTM D5338	n/a	Up to 18 months
Ecotoxicity	EPA 2021.0	%	96-hr LC50 > 100%
Effluent Turbidity	Large Scale ⁴	NTU	< 100
Biodegradability	ASTM D5338	%	100
Product Composition	Typical Value		
Thermally Processed Wood Fiber ⁶ (within a pressurized vessel)	80 % \pm 3 %		
Crosslinked Biopolymers and Water Absorbents	10 % \pm 1 %		
Crimped, Man-Made Biodegradable Interlocking Fibers	5 % \pm 1 %		
Micro-Pore Granules	5 % \pm 1 %		

* When uniformly applied at a rate of 3500 pounds per acre (3900 kilograms/hectare) under laboratory conditions. 1. ASTM test methods developed for Rolled Erosion Control Products that have been modified to accommodate Hydraulic Erosion Control Products. 2. Cover Factor is calculated as soil loss ratio of treated surface versus an untreated control surface. 3. % Effectiveness = One minus Cover Factor multiplied by 100%. 4. Large scale testing conducted at Utah Water Research Laboratory. For specific testing information please contact a Profile technical service representative at 866-325-6262. 5. Functional Longevity is the estimated time period, based upon field observations, that a material can be anticipated to provide erosion control and agronomic benefits as influenced by composition, as well as site-specific conditions, including; but not limited to - temperature, moisture, light conditions, soils, biological activity, vegetative establishment and other environmental factors. 6. Heated to a temperature greater than 380 degrees Fahrenheit (193 degrees Celsius) for 5 minutes at a pressure greater than 50 psi (345 kPa) in order to be Thermally Refined[™]/Processed and to achieve phyto-sanitization.

Packaging Data

Properties	Test Method	Units	Nominal Value
Bag Weight	Scale	kg (lb)	22.7 (50)
Bags per Pallet	Observed	#	40

UV and weather-resistant plastic bags. Pallets are weather-proof stretch wrapped with UV resistant pallet cover.

Distributed by: Quick Supply Co., 6620 NW Toni Drive Des Moines, IA 50313, Phone: (515)289-1271, www.quicksupplydm.com



Profile Products
750 Lake Cook Road, Ste. 440
Buffalo Grove, IL 60089
800-508-8681
www.profileproducts.com

To the best of our knowledge, the information contained herein is accurate. However, Profile Products cannot assume any liability whatsoever for the accuracy or completeness thereof. Final determination of the suitability of any information or material for the use contemplated, of its manner of use and whether the suggested use infringes any patents is the sole responsibility of the user.